



am TILEBOND

DESCRIPTION

am TILEBOND is a specially formulated cementitious tile adhesive. It is used for fixing floor and wall tiles. When used with **am** LATEX 330/302, it gives improved adhesion and water-repellent properties when set and hardened.

USES

am TILEBOND can be used as thin or thick bed adhesive for tiling on concrete and cement rendered surfaces. **am** TILEBOND is ideal for the installation of mosaics, marble, granite, ceramics, and homogeneous tiles. It is best used with **am** LATEX 330/302 for water tank and swimming pools, wet locations.

ADVANTAGES

- Pre-packed to ensure high consistency.
- Excellent workability and open time.
- For internal and external use.
- Suitable for ceramic and most natural stone tiles.

METHOD OF USE

Surface Preparation

Ensure that dust, oil and foreign materials are removed. Site practices like washing of the substrate a day before plastering is highly encouraged. Dampen dry concrete surface before application.

Mixing

Add approximately 5.5 Litres of water to 25kg of **am** TILEBOND. Mixed thoroughly using an electrical paddle mixer until homogenous soft paste is achieved. The pot life of the mixture is approximately 2 hours.

am LATEX 330/302 can be added to replace water for improved adhesion and effectiveness, when fixing large flat-based tiles and existing glazed surfaces.

Application

am TILEBOND can be applied onto sound substrate using a notched trowel or it can be applied onto the back face of the tiles using "Buttering Method". Both methods can be adopted when laying big tiles and tiles with deep grooves or ridges. After application, the tiles should be firmly pressed and knocked into position.

For tiling areas over movement joints, the joint should go right through the tile and adhesive bed.

HANDLING

am TILEBOND is non-hazardous. In windy conditions, wear a filter mask to avoid inhaling the powder. Remove splashes from skin with plenty of water. In case of eye contact, wash with plenty of water. If irritation persists, seek immediate medical attention.

SPECIFICATIONS			
Appearance	Grey or White		
Density • Dry • Mixed	1230 kg/m ³ 1820 kg/m ³		
Binder	Portland Cement		
Filler	Graded Silica Sand		
Water Powder Ratio	0.22		
Tensile Adhesion Bond Strength	BS EN 12004:2001 Requirements on Normal Set Adhesive (N/mm ²)	am Tilebond with Am Latex 330/302 (N/mm ²) EN-C2ES1	am Tilebond with Water (N/mm ²) EN-C1E
After 28 days under standard laboratory conditions	≥ 0.5	2.43	2.09
After 7 days under standard laboratory conditions, followed by 21 days immersed in water	≥ 0.5	1.38	1.11
After 14 days under standard laboratory conditions, followed by 14 days in oven (After Heat Aging)	≥ 0.5	2.48	0.80
Open Time after not less than 20 minutes	≥ 0.5	1.22	
Open Time at 30 minutes	≥ 0.5		0.57

CONSUMPTION

Approximately 2.3 kg to 4.6 kg per m².

PACKING

am TILEBOND is supplied in 25kg bags at 60 days per pallet.

SHELF LIFE

If stored in a cool and dry place, the shelf life of **am** TILEBOND is approximately 12 months in unopened bags.



Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8866

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn

Revised 3-Aug' 2020



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us. The user is responsible for checking the suitability of these products for its intended use.

