

HERTRON DENSIFIER

PRODUCT DESCRIPTION

HERTRON DENSIFIER is a blend of inorganic polymer materials that penetrates cementitious surfaces to increase density and hardness. **HERTRON DENSIFIER**'s proprietary formulation of reactive nano-sized particles, penetrates deeply into concrete surfaces bonding with the cement components of the slab. **HERTRON DENSIFIER** makes an extremely hard, dense surface that has increased wear resistance to foot and fork lift traffic. It is water based and environmentally friendly and is VOC compliant in all states.

PRIMARY APPLICATIONS

HERTRON DENSIFIER can be applied over existing or cured concrete, or while the slab is still green just after final trowel. **HERTRON DENSIFIER** can also cementitious wear toppings.

- Interior or exterior concrete
- Warehouses / Distribution centers
- Residential and garages Commercial floors
- Schools / Institutional
- All concrete surfaces

BENEFITS

- Meets all VOC regulations including California
- Permanently bonds to concrete
- Prevents dusting
- Does not 'white' if over used or not removed
- Reduces costs by saving labor and time
- Improves durability long term.

PHYSICAL PROPERTIES

Appearance	Clear tinted liquid
Drying time	20 min to 1 hour
p.H	~ 9.5
V.O.C content	0 g / L
Freeze point	32°F (0°C)
Shelf life	1 years
Coverage	400-600 f2/G (37-55 m ² /3.78L) 10-15 M²/L

PACKAGING

- Bucket, apx 5 gallon or 19 liter
- Drum, apx 55 gallon or 209 liter
- Tote, apx 270 gallon or 1022 liter

STORAGE

HERTRON DENSIFIER should be stored tightly sealed in its original container in a cool dry place life. Shelf life is approximately 1 year.

CLEAN - UP

Clean tools and equipment with water immediately after use. Residue from application and clean-up is non-toxic. Protect metals, glass, wood, paint or brick from contact with **HERTRON DENSIFIER**. If surface is accidentally over sprayed, wash immediately with potable water.

CAUTION

Keep out of reach of children. For professional use only. Read the material safety data sheet (MSDS) before handling or using. Follow recommended safety procedures while handling or using.

APPLICATION / DIRECTIONS

HERTRON DENSIFIER can be applied to concrete of any age. Surface must be clean and structurally sound. Surface also must be clear of membrane forming curing compounds, oils, dust and other surface contaminants.

DIAMOND GRINDING / POLISHING

Application typically is performed between the 80 and 400 grit stages depending on the surface conditions and the tools used. Use a low pressure sprayer to apply **HERTRON DENSIFIER** to form an even sheen across surface to ensure complete saturation of surface. Apply enough **HERTRON DENSIFIER** to keep the surface wet for 15 to 20 minutes. Let surface dry 1 hour before continuing.

NEW CONCRETE (GREEN)

HERTRON DENSIFIER may be applied to newly installed concrete after final trowel while slab is still Green. Slab must be clean and free of all materials such as curing compounds, bond breakers, release oils, dust and debris, etc. Use a low pressure sprayer to achieve a consistent, even application and consistent coverage of the surface. Reapply as necessary to keep surface wet for 20 minutes. Let surface dry. No cleaning, flooding, neutralizing, or rinsing is necessary.

MAIN TENANCE

Only an approved maintenance regimen should be used. Consult Hertron Solutions for more information. Cleaning solutions should be neutral pH. Avoid acidic cleaners and detergents containing hydroxides or sulfates as these may etch or dull the surface.

WARRANTY

HERTRON Solutions, Inc. ("**HERTRON**") warrants for 12 months from the date of shipment by Hertron or for the duration of the published product shelf life, whichever is less, that at the time of shipment by **HERTRON**, the product is free of manufacturing defects and conforms to **HERTRON**'s properties in force on the date of acceptance by Hertron of the order. If Hertron, in its sole discretion, determines that the product breached the above Warranty, it will, in its sole discretion, replace the non-conforming product or refund the purchase price. Please contact **HERTRON** for additional detail or clarification.

<http://www.hertroninternational.com/>

Contact Us

Louisiana
3120 Kansas Avenue
Kenner, LA 70065

Office:
504-382-1201
800-438-5066
Fax: 504-441-8873

North Carolina
306 Clanton Road
Charlotte, NC 28217

Office:
704-523-6722
800-438-5066
Fax: 704-532-6729

Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8666

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn



022-021
Eco-Friendly Building Material
Minimum 20% Recycled Content

Revised 3-Aug' 2020



ISO 9001:2000 Cert.No. 821853a



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us. The user is responsible for checking the suitability of these products for its intended use.