

am FLEXPROOF 501 DIY

DESCRIPTION

am FLEXPROOF 501 DIY is cement based flexible waterproofing membrane.

am FLEXPROOF 501 DIY is a two-part system consists of a liquid polymer and cement based powder component supplied in ready-to-use kit.

am FLEXPROOF 501 DIY will provide a tough elastic and waterproof membrane that can be coated onto concrete or masonry surfaces to prevent the ingress of water and moisture.

USES

am FLEXPROOF 501 DIY provides a seamless finish onto all types of concrete and masonry surfaces. It can be use for roofs, wet rooms, parking decks, basements, lift pits and areas affected by the ingress of water.

ADVANTAGES

- Able to bridge cracks up to 1mm wide.
- Can be applied on damp substrates.
- No application of primer is needed on the receiving substrate.
- **am FLEXPROOF 501 DIY** is able to withstand foot traffic when cured.
- Premixed to ensure high consistent quality.
- Protection of concrete structures in marine environment.
- Non-toxic and odourless, highly suitable for confined areas.

METHOD OF USE

Surface Preparation

Ensure all surface where **am FLEXPROOF 501 DIY** is to be applied must be free from oil, grease, wax and loose materials. For area where water absorbent is expected to be high, damp surface before applying **am FLEXPROOF 501 DIY**.

Mixing

Pour Part B (liquid component) into a clean container. Add Part A (powder component) slowly that allows mixing with a low-speed mechanical (350-450 rpm) until **am FLEXPROOF 501 DIY** is a homogeneous paste and is free of lumps.

Application

am FLEXPROOF 501 DIY can be applied with a stiff brush, a roller and can be trowelled on. For trowel application, the substrate should be leveled and free of any undulation (e.g. Potholes). During application ensure that air is not entrapped within the membrane.

After application of the first coat of **am FLEXPROOF 501 DIY**, allow it to cure for about an 1- 3 hour and ensure that the first coat has initial set before applying the second coat. Thickness of each coat can be between 1mm – 2mm.

Curing

Protect the surface of the coating from strong sunlight and drying winds with Polyethene sheets or other similar protective coverings.

CLEANING

am FLEXPROOF 501 DIY can be removed from tools and equipment with clean water. When **am** FLEXPROOF 501 DIY is cured, it can only be removed mechanically.

HANDLING

am FLEXPROOF 501 DIY should be stored in a dry place under shade, free from moisture contact.

am FLEXPROOF 501 DIY is non-hazardous. During windy conditions, wear a filter mask to avoid inhaling powder component from part A. Remove splashes from skin with water. In case of eye contact, wash with plenty of water. If irritation persists, seek immediate medical attention.

CONSUMPTION

Dosage is 2.0 to 3.0 kg/m² depending on the membrane thickness and the substrate. Average 1.8 to 2.0 Kg/m² for 1mm thickness.

PACKING

Pail 23 kg/set (17.5 kg per bag + 5.5 litres of Liquid Polymers)

SHELF LIFE

am FLEXPROOF 501 DIY has a shelf life of 12 months in tightly closed original packing.

SPECIFICATIONS

Consistency for application	Co-polymer modified cement slurry paste
Appearance	Grey
Mixed Density	1890 kg/m ³
Pot Life at 30°C	1 to 4 hours depending on temperature and wind conditions
Tensile Strength	1.0 N/mm ² (ASTM D412)
Elongation at Break	> 60% (ASTM D412)
Adhesion to Substrate	> 1 N/mm ²
Crack Bridging	Up to 1mm (ASTM C836)
Hardness (Shore A)	65
Water penetration test at 0.4 bars for 6 hours	No Penetration
Chemical Resistance	0.5% (v/v) NaCl 1.25% (v/v) NH ₄ OH 3.7% (v/v) HCL



022 - 021
Eco-Friendly Building Material
Minimum 20% Recycled Content

Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8866

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn

Revised 3-Aug' 2020



ISO 9001:2000 Cert.No. 421453a



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us. The user is responsible for checking the suitability of these products for its intended use.