

am FLEXPROOF 504 PU

DESCRIPTION

am FLEXPROOF 504 PU is a one component, liquid cold applied, highly permanent elastic, polyurethane waterproofing membrane. It cures by reaction with ground and air moisture.

USES

am FLEXPROOF 504 PU provides a seamless finish onto all types of concrete and masonry surfaces. It can be use for roofs, balconies, terraces, wet rooms, flowerbeds, planter boxes, bridge-decks, tunnels, etc., affected by the ingress of water.

ADVANTAGES

- Simple application (roller or airless spray)
- Able to bridge cracks up to 2mm wide, even at -10°C.
- Provides water vapour permeability.
- Full surface adherence without any additional anchoring.
- **am** FLEXPROOF 504 PU is able to withstand foot traffic when cured.
- Even if the membrane gets damaged, it can be easily repaired within minutes.
- Maintains its mechanical properties over a temperature span of -30°C to +90°C.

METHOD OF USE

Surface Preparation

Ensure all surface where **am** FLEXPROOF 504 PU is to be applied must be free from oil, grease, wax and loose materials, which may harmfully affect the adhesion of the membrane. Maximum moisture content should not exceed 5%. New concrete structure need to dry for at least 28 days. Do not wash surface with water.

Repair of Cracks and Joints

The careful sealing of existing cracks and joints before the application is extremely important for long lasting waterproofing results.

Clean concrete cracks and hairline cracks of dust, residue or other contamination. Prime locally with UP – 100 PRIMER and allow 2 to 3 hours to dry. Fill all prepared cracks with **am** SEAL PU1 or appropriate sealants. Then apply a layer of **am** FLEXPROOF 504 PU, 200mm wide centered over all cracks and while wet, cover with a 100mm cut stripe of glass fibre mesh. Press it to soak. Then saturate the fibre mesh with enough **am** FLEXPROOF 504 PU until it is fully covered. Allow 12 hours to cure.

Priming

Prime absorbent surfaces like concrete, cement screed or wood with UP – 100 PRIMER. Allow the primer to cure.

Application

Stir well before use.

am FLEXPROOF 504 PU can be applied by roller, brush or airless spray on the primed surfaces.

Reinforce always with glass fibre mesh at problem areas, such as wall-floor connections, pipes, waterspouts.

Each layer of **am** FLEXPROOF 504 PU should be cured for 12 hours (not later than 36 hours) before applying the next layer. Do not apply **am** FLEXPROOF 504 PU over 0.6mm thickness (dry film) per layer.

HANDLING

am FLEXPROOF 504 PU should be stored in a dry place under shade, free from moisture contact.

am FLEXPROOF 504 PU contains isocyanates. Remove splashes from skin with water. In case of eye contact, wash with plenty of water. If irritation persists, seek immediate medical attention.

CONSUMPTION

1.5 to 2.5 kg/m² applied in two or three layers depending on surface porosity and application method.

PACKING

am FLEXPROOF 504 PU is supplied in white, grey, red and green in 20kg pail.

SHELF LIFE

am FLEXPROOF 504 PU has a shelf life of 06 months.

SPECIFICATIONS	
Composition	Polyurethane high-solids pre-polymer
Elongation at Break	> 550% (ASTM D 412)
Tensile Strength	≥2.0 N/mm ² (ASTM D 412)
Water Vapour Permeability	25 ± 4 gr/m ² /day (ISO 9932:91)
Resistance to Water Pressure	No Leak (1m water column, 24 hr) (DIN EN 1928)
Adhesion to concrete	> 1.5 N/mm ² (ASTM D 903)
Shore A Hardness	65 ± 5 (ASTM D 2240)
Rain Stability Time	4 hours (at 20°C, 50% RH)
Light Pedestrian Traffic Time	12 hours (at 20°C, 50% RH)
Final Curing Time	7 days (at 20°C, 50% RH)
Chemical Properties	Good resistance against acidic and basic solutions (10%), detergents, seawater and oils



Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8866

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn

Revised 3-Aug' 2020



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us, The user is responsible for checking the suitability of these products for its intended use.