

am POLYTHANE 400 (HF/MF/GF)

A heavy duty, smoothing or slip resistant polyurethane screed, floor

DESCRIPTION

am Polythane HF/MF/GF is a multi-component Polyurethane trowel and flow applied in average thickness from 3-9mm for industrial application and repairing in matt anti-skid finish offering versatility in performance, aesthetic and cost effective.

USES & ADVANTAGES

am Polythane HF/MF/GF is used extensively in the following areas:

Hygienic floor for kitchen, wet floor, beverage, processing and packaging plants.

Anti-skid finish for safety in slippery or oily services conditions.

Thermal shock, chemical resistance floor for chiller, oven installed areas or chemical process.

- Food production
- Meat processing
- Vegetable and fruit canning
- Dairy products, bakeries and confectioners
- Chemical production and processing
- Textile production - bleaching and dying
- Metal processing and engineering

am Polythane HF/MF/GF is providing :

Excellent chemical resistance, high temperature resistance(up to 120oC and anti skid for safety purposes.

Maximum wear, abrasion and impact resistance.

User-friendly, easily cleaned and maintained surface. Resists bacterial growth, fungi, mildew.

Seamless without joints for sanitation, hygienic finish and Food Grade.

am Polythane HF/MF/GF is available in standard colors such as Yellow, Light Grey, dark green and Red.

As a direct result slight yellowing of the floor surface exposed to UV may occur especially in light colors without affecting its performances or functionality.

Packaging

am Polythane HF/MF/GF systems is supplied in different packs and sizes for primer coat / topcoats with resin A, hardener B and filler C and pigment D for chosen product.

Typical Data of Hardened Material

Density	2.0 Kg/mm/m2
Thermal conductivity	1.0 W/m oC
Compressive strength	62 N/mm2
Tensile Strength	7 N/mm2
Flexural strength	15 N/mm2
Bonding strength	Concrete Failure
Dynamic Elastic Modulus	2000 N/mm2
Taber Abrasion resistance	0.1gm/1000gm/100rpm
Coefficient of linear thermal expansion	25 x 10-5oC
Impact resistance	<0.5(BRE Screed Tester)mm
Temperature resistance	-40oC-120oC (9mm)
Water absorption	0 ml
Pot life	25 Min @ 15oC 35 Min@8oC

Application Procedure Preparation:

am Polythane HF/MF/GF must be applied to a clean, dry substrate free from dust, dirt, oil, grease and other contaminants.

Existing concrete:

Old floor needs thorough inspection for its integrity providing an ideal substrate for maximum bonding. Surface has to be free from all contaminants. Grooves of approximately 5mm wide and 5mm deep have to be created diagonally into the floor every 1.5m to facilitate mechanical bonding.

For best performances should not be applied to concrete, which contains more than 5% moisture by mass. The substrate can be considered sufficiently dry only when the Relative Humidity (RH) at the surface falls to 75% or less when measured with a hygrometer to BS 8201: 1987 Appendix A.

New construction:

Floors to be overlaid should be at least 28 days old. The removal of laitance and contaminants is best achieved by mechanical means, such as vacuum recovery shot blasting or scarifying.

Service temperatures is from -40oC up to 120oC and depending on thickness but only may be up to 120oC on intermittent splash.

Installation temperature should not be applied on floor or substrate temperature below 10oC. Temperature should not fall below 5oC in the 24 hours after application.

Curing conditions

Foot traffic 10 hours @25oC / 8 hours @ 35oC
Light traffic 24 hours @25oC / 18 hours @ 35oC

Full traffic 48 hours @25oC / 24 hours @ 35oC

Full cure 7 days @25oC / 5 days @ 35oC

All moving joints must be carried through the

am Polythane HF/MF/GF and properly sealed. Construction joints and cracks may be covered but if substrate movement occurs, the

am Polythane HF/MF/GF will reflect the crack.

Maintenance

Regular cleaning and maintenance will prolong the life of all resin floors, enhance the appearance and reduce the tendency to retain dirt.

Only use clean water to wash the floor for the first 5 days from the completion date and can use liquid light diluted soap, detergent with pressure water to wash the floor.

Storage & Shelf Life

Store out of direct sunlight, clear of the ground, on pallets protected from rainfall. Up to 12 months if stored in unopened containers.

Safety Precautions

As with all chemical products, care should be taken, during use and storage, to avoid contact with eyes, mouth, skin and foodstuffs. Treat splashes to eyes and skin immediately. If accidentally ingested, seek medical attention.

Cleaning

Uses thinner, acetone, xylene or other solvent to clean tools prior to material taking a hard set.

Asia Mortar Co., LTD (AM Co., LTD)

33/1 Ly Van Phuc, Tan Dinh Ward, Dist. 1, HCMC

Tel: (84-8) 38208686 Fax: (84-8) 38208866 Email: amv@asiamortar.com Website: www.asiamortar.com