

am SKIM

DESCRIPTION

am SKIM is a cement based skim coat which is suitable for plastered surfaces, precast ceiling components and other concrete surfaces for internal and external applications. It comes in both grey and white colours.

am SKIM is designed to provide a smooth durable finish together with excellent adhesion strength. It meets the stringent architectural requirements for high quality and fine finishes.

USES

am SKIM is highly recommended for all type of concrete substrates such as precast ceilings, lightweight panel, walls, columns and beams. It is also excellent for lightweight autoclaved aerated blocks, blockwalls and plastered surfaces.

ADVANTAGES

- Premixed to ensure high consistent quality.
- Convenience in handling.
- Same amount of water is added to achieve consistency in workability.
- Easy Mixing and application.
- Excellent bond strength.
- High durability and good weather resistance.
- Cleaning limited to just disposing used paper bag.

METHOD OF USE

Surface Preparation

Ensure that dust, oil and foreign materials are removed. Site practices like washing of the substrate a day before plastering is highly encouraged. Dampen dry concrete surface before application.

Mixing

Add approximately 11.6 litres of water to 40kg of **am SKIM**. Mix thoroughly using an electrical paddle mixer for 3 minutes until a homogenous slurry paste is achieved. When it is free of lump, the skim coat is ready for use.

Application

am SKIM is applied using a steel trowel or it can be machine sprayed. After mixing, it will remain workable for approximately 60 minutes. Do not add additional water to existing unused skim coat mix.

If **am SKIM** is to be applied onto a plastered surface, it can do so once the plastered surface has achieved initial set.

am SKIM allows for both trowelled and brush finish.

HANDLING

am SKIM should be stored in a dry place. In case of eye contact, wash with plenty of water. If irritation persists, seek immediate medical attention.

SPECIFICATIONS	
Water Powder Ratio	Approximately 0.29 (or 11.6 litres of water per 40kg bag)
Appearance	Grey or White
Water Retentivity	>95 % (BS 4551 : Part 1 : 1998)
Consistency	Homogeneous mortar paste
Binder	Cement
Filler	Graded Calcium Carbonate
Additives	Polymer for workability, water retention and adhesion
Density	
• Dry	1260 kg/m ³
• Mixed	1510 kg/m ³
Recommended Thickness	1mm to 3mm per layer of application. For layers exceeding 5mm of thickness, am RENDER is recommended prior to finishing with am SKIM.

CONSUMPTION

A 40kg bag yields approximately 34 litres of **am** SKIM mix.

PACKING

am SKIM comes in 40 kg bag at 40 bags per pallet.

SHELF LIFE

If stored in cool and dry place, the shelf life of **am** SKIM is approximately 12 months from date of manufacture in unopened bags.



Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8866

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn

Revised 3-Aug' 2020



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us, The user is responsible for checking the suitability of these products for its intended use.