

am TILEBOND FS

DESCRIPTION

am TILEBOND FS is a high quality fast set 2 -part cement-based tile adhesive designed for both internal and external tiling to walls and floors.

USES

am TILEBOND FS can be use as thin or thick bed adhesive for tiling on concrete, cement rendered surfaces. **am** TILEBOND FS is ideal for the installation of mosaics, marble, granite, ceramics and homogeneous tiles.

ADVANTAGES

- Premixed to ensure high consistent quality delivered to site.
- Mixing by just adding both Part A (dry powder) and Part B (liquid polymer).
- Excellent bond strength.
- Long open time.
- Water resistance.
- High workability enabling easy laying of tiles.

METHOD OF USE

Surface Preparation

Ensure that dust, oil, wax and curing material are removed. Rendered surface should be free from loose plaster and concrete substrate should be free from heavy movement and other contamination materials.

Mixing

Add approximately 5 litres of liquid polymer to 25 kg bag of **am** TILEBOND FS. Mix thoroughly using an electrical paddle mixer for 1-3 mins until a homogeneous mixture that is free of lump is achieved.

Application

am TILEBOND FS can be applied onto sound substrate using a notched trowel or it can be applied onto the back face of the tiles (Buttering Method). Both methods can be adopted when laying big tiles and tiles with deep grooves or ridges. After application, the tiles should be firmly pressed and knocked into position.

Choice of notch trowel should be governed by the depth of knobs, grooves or ridges on the back of the tiles and the evenness of the substrate. Spread the adhesive onto the substrate using a 6 mm x 6 mm notched trowel for walls, and a 10 mm x 10 mm or 12 mm x 12 mm notched trowel for floor tiles. A 6 mm x 6 mm notched trowel is recommended for mosaic tiles. Ensure that there are no voids under the tiles. For tiling areas over movement joints, the joint should go right through the tile and adhesive bed.

HANDLING

am TILEBOND FS is non-hazardous. In windy conditions, wear a filter mask to avoid inhaling the powder. Remove splashes from skin with plenty of water. In case of eye contact, wash with plenty of water. If irritation persists, seek immediate medical attention.

SPECIFICATIONS	
Appearance	Grey
Density	1600 kg/m ³
Binder	Portland Cemen
Filler	Graded Silica Sand
Open Time	20 minutes
Tensile Adhesion Bond Strength	0.69 N/mm ² 1.10 N/mm ²
• At 6 hours	
• At 24 hours	
Adjustability Test	0.69 N/mm ² 1.10 N/mm ²
• At 5 minutes	
• At 10 minutes	
Water Absorption	7.2%

CONSUMPTION

Approximately 1.6 kg per m² per mm thick.

PACKING

am TILEBOND FS is supplied in 25kg Powder (Part A) and 5 Litres Liquid Polymer (Part B).

SHELF LIFE

If stored in a cool and dry place, the shelf life of **am** TILEBOND FS is approximately 6 months in unopened bags.



022 - 021
Eco-Friendly Building Material
Minimum 20% Recycled Content

Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8866

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn

Revised 3-Aug' 2020



ISO 9001 : 2000 Cert.No. : 821853a



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us, The user is responsible for checking the suitability of these products for its intended use.