

LYTHIC DAY 1

PRODUCT DESCRIPTION

Lythic DAY 1 is designed to assist with the finishing of interior and exterior concrete. Typically applied, **DAY1** will lubricate the slab surface, increasing the efficiency of power trowels, and extending the workability time for the final trowel. Improved troweling leads to better slab consolidation resulting in increased strength and durability. **DAY1** reacts with calcium hydroxide and silica components of the slab resulting in a densified, dust-proofed, abrasion resistant surface.

PRIMARY APPLICATIONS

Applications include but are not limited to concrete floors, walls, driveways, sidewalks, precast stone, masonry and natural stone.

- Bridges and Roads
- Parking Garages
- Interior or exterior concrete
- All concrete surfaces

BENEFITS

- Water based, low VOC content
- Simple, spray application
- Increases the efficiency of power trowels
- Less fatigue on both the trowel and the operator
- Prevents dusting and efflorescence
- Improves abrasion resistance, long term durability
- Will repel water from the surface
- Will inhibit salt penetration
- Reduces alkali-silica reaction (ASR) potential
- Will accept other surface treatments with no special prep

PHYSICAL PROPERTIES

Appearance	Milky white liquid
V.O.C content	0 g / L
Total solids	50 – 60%
p.H	9.5 – 10.5
Freeze point	32°F (0°C)
Shelf life	1 year
Coverage	See “application/directions” for details

PACKAGING

Bucket, apx 5 gallon or 19 liter
 Drum, apx 55 gallon or 209 liter
 Tote, apx 270 gallon or 1022 liter

STORAGE

Lythic DAY 1 should be stored tightly sealed in its original container at 40-80 degrees F. to maximize shelf life. Shelf life is approximately 1 year.

CLEAN -UP

Clean tools and equipment with water immediately after use. Residue from application and clean-up is non-toxic. Protect metals, glass, wood, paint or brick from contact with **Lythic DAY1**.

CAUTION

Keep out of reach of children. For professional use only. Read the material safety data sheet (MSDS) before handling or using. Follow recommended safety procedures while handling or using.

APPLICATION / DIRECTIONS

Lythic DAY1 can be applied as part of placement or 24 hours after.

- Always mix **DAY1** well, before using or diluting, preferably with a mechanical mixer paddle.
- 4:1 , The recommended dilution rate is 1 part DAY1 to 4 parts potable water.

WET / TROWEL- IN APPLICATION

Lythic DAY1 is applied to newly installed concrete during the final trowel. Use a low pressure sprayer to apply **DAY1** ahead of power trowel to increase trowel efficiency and create greater surface consolidation. Coverage is apx 200-300 ft² per gallon.

AFTER SLAB PLACEMENT

Lythic DAY1 may be applied after slab placement. Use a low pressure sprayer to achieve a consistent, even application. Apply product to sufficiently “wet” the surface while not allowing to puddle. If needed, follow spray application by broom to avoid puddling and the wasting of material.

Coverage is apx 400-500 ft² per gallon

Product dries quickly. Apply so as to maintain a wet edge. Otherwise, water spotting may occur and/or product is wasted..

WARRANTY

Lythic Solutions, Inc. (“**Lythic**”) warrants for 12 months from the date of shipment by **Lythic** or for the duration of the published product shelf life, whichever is less, that at the time of shipment by **Lythic**, the product is free of manufacturing defects and conforms to **Lythic’s** properties in force on the date of acceptance by **Lythic** of the order. If **Lythic**, in its sole discretion, determines that the product breached the above Warranty, it will, in its sole discretion, replace the non-conforming product or refund the purchase price. Please contact **Lythic** for additional detail or clarification.

www.lythic.net

PO Box 5028

Vancouver, WA 98668

888-598-4421 t

+1 360-694-5347 v

+1 360-828-7950 f



Nano-Silica Technology
for Concrete



022 - 021
Eco-Friendly Building Material
Minimum 50% Recycled Content

Asia Mortar Co., LTD (AM Co., LTD)

Tel: (84-028) 38 20 8686 Fax: (84-028) 38 20 8666

Email: amv@asiamortar.com.vn Website: www.asiamortar.com.vn

Revised 3-Aug' 2020



ISO 9001 : 2000 Cert.No. 421853a



This information in this catalogue is provided to the best of our knowledge from results gathered both internal and external credited laboratories. However, we have no control over site applications, site conditions and workmanship of the applicator. We therefore will not accept any liability, either directly or indirectly arising from the misuse of these products or when the product is used not in accordance with any advice, specification, and recommendation of information given by us. The user is responsible for checking the suitability of these products for its intended use.